



Product overview

Quietspace® Panel is a high-performance acoustic treatment engineered to absorb a minimum of 85% of the sound energy it meets. Made from 100% polyester fibre, Quietspace Panel has a hard, compressed face and cushioned backing, available in 25 mm, 50 mm, 75 mm, and 100 mm thicknesses.

Sustainable material

- Carbon neutral product
- Zero carbon manufacturing
- Recycled content - >60% recycled material
- Low VOC and CDPH compliant - <0.035 mg/m³ (7 days)
- Zero waste manufacturing initiative
- Sustainable supply chain and anti-modern slavery

Environmental certifications

- EPD – compliant with ISO 14025 and ISO 15804
- Declare – Red List free (third party verified)
- ISO 14001 Certified Environmental Management
- Health Product Declaration
- CDPH Standard



Certifying your green building

Autex Acoustics products meet criteria for WELL, LEED, Green Star, and BREEAM building rating systems, helping you achieve certification for your project. For support and guidance on available rating system points please visit www.autexglobal.com, or speak with your Autex Acoustics account manager.

Specification

(Wall/Ceiling) treatment shall be Quietspace® Panel made from thermally bonded polyester containing no less than 45% recycled material as manufactured by Autex www.autexglobal.com

Panel 1200 mm x 2400 mm x ()mm nom depth, sound absorption: 25 mm: Class C, NRC 0.85, 50 mm: Class A, NRC 1.00. Fire rating fullk range of thicknesses: ISO9705:

Classification: Group 1-S, AS ISO 9705 – 2003: Group 1, 25 mm BS EN 13501-1:2018: B - s2, d2

Install as per Autex Acoustics recommendations. If Quietspace Panel is to be specified for use other than as a ceiling or wallcovering please seek guidance from your specification manager.



Product specifications

Product name	Quietspace® Panel
Composition	100% polyester fibre (PET)
Panel dimensions	1200 mm x 2400 mm
Tolerance	(+ 5 mm) x (+ 10 mm)

Thickness	25 mm	50 mm	75 mm	100 mm
Tolerance	(+/- 6%)	(+/- 6%)	(+/- 6%)	(+/- 6%)
Weight	2300 gsm	3800 gsm	4050 gsm	4300 gsm

Installation

Install as per Autex Acoustics recommendations. Install instructions are included in each pack, or available on the website. If Quietspace Panel is to be specified for use other than as a wallcovering, please seek guidance from your specification manager. In situations where product is being installed near fire protection systems (e.g. sprinklers or fire alarms) relevant building codes, standards and design rules must be adhered to.

Please consult the project engineer and relevant expert such as a fire protection engineer.

Light reflectance

White Quietspace Panel is suitable for indoor use only and has a light reflectance value of 83 (measured in accordance with BS 8493:2008+A1:2010).

Thermal performance

(Internally tested by Autex Lab)

25 mm: R0.6 (@23°C)
50 mm: R1.4 (@23°C)
75 mm: R1.9 (@23°C)
100 mm: R2.4 (@23°C)

Product specifications

Fire ratings

Quietspace® Panel has been evaluated using the following test methods:

ISO 9705: 1993

Classification: Group 1-S

Smoke production rate:

<5.0m²/s

As required by NZBC C/VM2

AS ISO 9705 - 2003

Classification: Group 1

(SMOGR_{ARC}): <100m²/s²

Assessed using methodology AS ISO 9705:2003 in accordance with AS 5637:2015, as required by BCA Specification C110-4

FI 4871

FAR 4055

BS EN 13501-1:2018

(25 mm Quietspace® Panel)

Wall applications

Classification: B-s₂d₂

Tested using BS EN ISO 11925-2:2020 and BS EN 13823:2020 and classified in accordance with BS EN 13501-1:2018, as required by BS EN 15102:2007 + A1:2011.

EUI-21-000135-E-A

Ceiling applications

Classification: B-s₂d₂

Tested using BS EN ISO 11925-2:2020 and BS EN 13823:2020 and classified in accordance with BS EN 13501-1:2018, as required by BS EN 13964:2014.

EUI-21-000135-E-B

ASTM E84 - 14

(1" Quietspace® Panel)

Class A, FS:0 - SD:10

RJ3297

Water vapour sorption

ASTM C1104 / C1104M-13a

Test conditions: 49°C, 95%RH

Water vapour absorbed and

adsorped after 4 days:

0.4% by weight.

Pattern repeat

Non-woven. No pattern repeat

but product has directional

grain. Product may vary from

samples and batch to batch

due to fibre blending and

lay-up, which is an inherent

feature of this product.

Impact resistance

ISO 7892:1988

Hard body impact

There is no surface damage

or penetration to Quietspace

Panel when subjected to

hard body impacts. A small

indentation might be observed

when subjected to an impact

equivalent to the impact of a

0.5 kg object dropped from a

0.5 m height. When adhered to

10 mm plasterboard, the system

can resist a 14 joule impact,

and no further indentations are

observed. This is equivalent to

the impact of a 0.5 kg object

dropped from a 3 m height.

Soft body impact

There is no surface damage

or penetration to Quietspace

Panel when subjected to soft

body impacts. When adhered to

10 mm plasterboard, the system

can resist a 120 joule impact.

This is equivalent to the impact

of a 50 kg object dropped from

a 250 mm height.

Microbial resistance

ASTM G21-15

Growth rating: 0 (No growth)

Quietspace Panel does not

promote the growth of moulds

and mildew.

Fabric care

Blot spills from fabric quickly.

Wipe with a damp cloth. Avoid

rubbing and excessive amounts

of water as this will affect the

finish. Use carpet or upholstery

shampoo as directed. Blot

with a clean dry cloth after

each application of solution.

Custom printed Quietspace

Panel requires the services of

a specialist cleaning company.

Refer to the Quietspace Panel

Care and Maintenance Guide

for more information.

Service

For further information about Quietspace Panel or any other Autex Acoustics product, please contact your account manager or visit our website.



Acoustic performance

Quietspace Panel is specifically designed to reduce and control reverberated noise and echo in building interiors. Minimum Noise Reduction Coefficient 0.85

Frequency (Hz)	125	250	500	1000	2000	4000	NRC
● 25 mm	0.15	0.45	0.85	1.00	1.00	0.95	0.85
● 50 mm	0.30	0.75	1.10	1.10	1.05	1.00	1.00
● 75 mm	0.50	0.90	1.05	1.05	0.95	0.90	1.00
● 100 mm	0.65	1.00	1.05	1.00	0.95	0.90	1.00

Table presents the practical sound absorption coefficients as according to ISO 11654. Graph presents third octave sound absorption coefficients (according to ISO 354 measurement of sound absorption in a reverberation room). The NRC rating is determined as the arithmetic average of the absorption coefficients measured by one-third octave bands centred on 250 Hz, 500 Hz, 1000 Hz and 2000 Hz and rounded to the nearest 0.05.

Absorption Coefficient according to ISO 354 University of Auckland Testing Service

Quietspace Panel 25 mm - test no. T0712-18
Quietspace Panel 50 mm - test no. T1228-8
Quietspace Panel 75 mm - test no. T1905-4
Quietspace Panel 100 mm - test no. T1905-5

